

1. Description

Greemas® 70102 is a PLA (Poly lactide) based alloy with 70% PLA content and is certified as a biodegradable resin with a seed sprout and growth rate over 80% according to ASTM D6866. The processibility and toughness are greatly improved, and can be used in tableware and packaging.

2. Properties

General Properties

Item		Test Method	Unit	State	Data
Density	-	ISO 1183	g/cm ³	dry	1.24
Mass flow rate	(210 $^{\circ}$ C ,2.16kg)	ISO 1133	g/10min	dry	11
Linear mould shrinkage	(long.)	ISO 294	%	dry	0.10
Linear mould shrinkage	(trans.)	ISO 294	%	dry	0.35

Mechanical Properties

Item		Test Method	Unit	State	Data
Tensile strength at break	(10mm/min)	ISO 527-1,-2	MPa	cond.	32
Elongation at break	(10mm/min)	ISO 527-1,-2	%	cond.	120
Flexural strength at break	(2mm/min)	ISO 178	MPa	cond.	55
Flexural modulus	(2mm/min)	ISO 178	MPa	cond.	4500
Notched impact strength	(4mm, 23°℃)	ISO 179/1eA	KJ/m ²	cond.	5.6

Thermal Properties

Item		Test Method	Unit	State	Data
Melting point	(DSC)	ISO 11357	$^{\circ}\!\mathbb{C}$	dry	165
Heat deflection temperature DT/B	(0.45 MPa)	ISO 75	$^{\circ}\! \mathbb{C}$	dry	62
Heat deflection temperature DT/A	(1.80 MPa)	ISO 75	$^{\circ}\! \mathbb{C}$	dry	61

^{*} These property data are believed to be representative under specific test conditions and are not intended to serve as product specifications.

3. Applications

✓ Stationery ✓ Tableware ✓ Toys

✓ Food container ✓ Packaging ✓ Card applications

4. Drying Conditions

The drying temperature at $75 - 85^{\circ}$ C with a duration 3 - 4 hrs is recommended.

To obtain better product performance, a desiccant dryer is also recommended.



5. Recommended Processing Conditions

The following is the recommended injection molding conditions for the first trial:

Condition	Barrel Temp.	Nozzle Temp.	Mold Temp.	Screw Speed	Injection Pressure	Injection Rate	Holding Pressure
Value	190 – 210	190 – 210	< 40	50 – 100	85 – 100	80 – 90	85 – 100
Unit	$^{\circ}\!\mathbb{C}$	$^{\circ}$ C	$^{\circ}\!\mathbb{C}$	rpm	kg/cm ²	%	kg/cm ²

^{*}For extrusion sheeting process, the barrel temperature between 180 and 210°C is recommended, with configuring general purpose screws with L/D ratios from 24 to 30 and compression ratios between 2.5:1 and 3:1.

6. Recommended Storage Conditions

Store Greemas® 70102 in cool and dry place. Protect from direct sunlight, rain and violent temperature fluctuation. Fire is inhibited around storage area. No special restrictions on storage with other products. The recommended storage duration is five years.

7. Appearance and Packaging

Greemas®70102 is in pellet form with a package of 25 Kg net weight per paper bag.